

| Parameter | Substance | Bulk | Breaking Length | | Tear Factor | | Cobb/60 Sec. | Bendtsen Roughness | Brightness ISO | Opacity | Wax Pick | Shade |
|--|-----------------------------------|--|-----------------|----------|-------------|------|-------------------|---|----------------|---|-------------------------------------|------------------------|
| | | | MD | CD | MD | CD | | | | | | |
| Unit | gm/m ² | cc/gm | Meter | Meter | - | - | gm/m ² | ml/Min | % | % | No. | - |
| Century Book Printing | 54-60 70-80 | 1.66(Min) 1.66(Min) | 4500±500 | 2500±500 | 45±5 | 50±5 | 23±2 | 650±150 750±150 | 86±2 | 54 gsm - 80±1 >60 gsm - 84±1 | 14 A Clear | Natural |
| Century Dazzle Print | 54-60 64-80 120-140 | 1.35(Min) 1.30(Min) 1.27(Min) | 5000±500 | 2800±500 | 50±5 | 55±5 | 22±2 | 250±50/300±50 110±50/150±50 110±50/150±50 | 92±1 | 54 gsm - 87±1 57-60 gsm - 90±1 68-70 gsm - 95±1 >80gsm - 95 Min | 54-60 14A Clear 64-140 16A Clear | Brilliant Blue |
| Super White Maplitho (NSS) | 53-62 | 1.22(Min) | 4000±400 | 2400±400 | 42±5 | 48±5 | 21±2 | 100±30 150±30 | 88±1 | 53-54 gsm - 87±1 56-58 gsm - 88±1 60-62 hsm -89±1 | 12A Clear | Bluish |
| Super White Maplitho (SS) | 64 - 75 78-100 110-120 | 1.19(Min) 1.17(Min) 1.15 (Min) | 4200±500 | 2500±500 | 45±5 | 50±5 | 23±2 | 100±30 150±30 | 90±1 | Upto 70 gsm - 88±1 75 -90 gsm - 92±1 100 gsm & above -95±1 | 14A Clear | Bluish |
| Super White Maplitho (H.B)/Plain Paper | 54-60 68-70 78 - 80 | 1.22(Min) 1.19(Min) 1.17(Min) | 4000±400 | 2400±400 | 45±5 | 50±5 | 21±2 | 100±30 150±30 | 92±1 | Upto 57 gsm - 83±1 60-70 gsm - 87±1 80 gsm & above - 89±1 | 54-60-12A Clear 70-80-14A Clear | Bluish |
| Century Neria Print | 54-62 | 1.22(Min) | 4000±500 | 2400±500 | 42±5 | 48±5 | ≤23 | 130±30/180±30 | 90±1 | 54-58 gsm - 88±1 60-61 gsm - 90±1 62 gsm - 91±1 | 12 A Clear" | Bright Bluish |
| Century Neria Print | 64-75 78-100 110-120 | 1.19(Min) 1.17(Min) 1.15(Min) | 4000±500 | 2500±500 | 42±5 | 48±5 | 23±2 | 110±30/160±30 | 90±1 | 75-80 gsm - 93±1 90-100 - 95±1 110gsm & above - 97±1 | 14 A Clear | Bright Bluish |
| Enova Print (NSS) | 50-62 | 1.33(Min) | 4000±400 | 2400±400 | 45±5 | 50±5 | 20±2 | 160±30 200±30" | 88 ±1 | Upto 52 gsm - 88±1 54-58 gsm - 90 ±1 60 -62 gsm - 92±1 | 12A Clear | Bluish Reddish |
| Enova Print (SS) | 64-70 78-100 110-120 | 1.22(Min) 1.21(Min) 1.20(Min) | 4000±400 | 2400±400 | 45±5 | 50±5 | 23±2 | 150±30 190±30 | 88 ±1 | 64-70 gsm - 93±1 78-90 gsm - 95±1 100 gsm & above - 97±1 | 14A Clear | Bluish Reddish |
| Century Imperial Print | 57-64 68-90 100-120 | 1.25(Min) 1.22(Min) 1.17(Min) | 5000±500 | 2500±500 | 45±5 | 50±5 | 23±2 | 110±30 150±30 | 90±1 | 57-60 gsm - 90±1 64-68 gsm - 92±1 70-80gsm - 94±1 90 & above - 96±1 | 14A Clear | Bluish Reddish Bright |
| Century Pristine Maplitho | 57-64 68-70 75-90 90-120 | 1.25(Min) 1.24(Min) 1.23(Min) 1.17(Min) | 5000±500 | 2500±500 | 45±5 | 50±5 | 23±2 | 110±50 130±50 | 90±1 | 57-60 gsm - 90±1 64-68 gsm - 92 ±1 70-80gsm - 94±1 90 & above - 96±1 | 14A Clear | Brilliant Reddish tint |
| Century Bond | 85 | 1.32(Min) | 6300±500 | 3200±500 | 65±5 | 70±5 | 20±2 | 200±30/280±30 | 96±1 | 90±1 | 16 A Clear | Off White |

An ISO 9001 , ISO 14001 & OHSAS 18001 Company