

## Product Specification

S.No.	Properties		UOM	Product Quality : Century OGR	
1	Substance		g/m <sup>2</sup>	40 ± 2.5 %	45 ± 2.5 %
2	*Bulk		cm <sup>3</sup> /g	1.30 ± 0.03	1.30 ± 0.03
3	*Breaking Length	MD	meter	6500 ± 500	6500 ± 500
		CD		3500 ± 500	3500 ± 500
4	*Tear Factor	MD	-	60 ± 5	60 ± 5
		CD		65 ± 5	65 ± 5
5	Cobb <sub>60</sub>		g/m <sup>2</sup>	18 Max.	18 Max.
6	Smoothness (Bendtsen)	I side	ml/min	120 ± 30	120 ± 30
		II side		150 ± 30	150 ± 30
7	*ISO Brightness(L&W Elrepho)		%	80 min.	80 min.
8	*Grease Resistance		Kit No.	7 min.	7 min.
9	*Wax Pick		No.	18A Clear	18A Clear
10	Shade		-	Natural	Natural
11	Moisture		%	4.5 ± 0.5	4.5 ± 0.5

\*Note : If goes beyond higher side tolerance, Quality is OK.

Test Conditions : Temperature 23 ± 1°C & Relative Humidity 50± 2 % ( Tappi 402)

All properties are as per CPP Lalkua measurements

Tolerance are based upon 95 % confidence limits of single mill measurement on conditioned Random samples.

An ISO 9001,ISO 14001 & ISO 45001 Company.

Being an innovative organization, Century Pulp & Paper is continually working in response to customer requirements. The specification mentioned are therefore subject to change. Learn more about our upgraded specification sheet on our website : [www.centurypaperindia.com](http://www.centurypaperindia.com)

Date : 01.06.2024

Note : This specification supersedes all previous specification