



Product Specification

Product Quality : Overlay Tissue

S.No.	Properties	UOM	Product Quality
1	Substance	g/m ²	45 ± 2.5 %
2	*Bulk	cm ³ /g	1.20 ± 0.03
3	*Burst Factor	-	30 ± 5
4	*Breaking Length	MD	7000 ± 500
		CD	4000 ± 500
5	*Tear Factor	MD	65 ± 5
		CD	75 ± 5
6	*Double Fold	MD	80 ± 10
		CD	40 ± 10
7	Smoothness (Bendisen)	I side	120 ± 30
		II side	150 ± 30
8	*ISO Brightness(L&W Erepho)	%	85 ± 1
9	Wet Tensile Strength (Min)	MD	1000 ± 50
		CD	650 ± 50
10	Shade	-	Natural
11	Moisture	%	4.5 ± 0.5

*Note : If goes beyond higher side tolerance, Quality is OK.

Test Conditions : Temperature 23 ± 1°C & Relative Humidity 50± 2% (Tappi 402)

All properties are as per CPP Lalkua measurements

Tolerance are based upon 95 % confidence limits of single mill measurement on conditioned Random samples.

An ISO 9001, ISO 14001 & ISO 45001 Company.

Being an innovative organization, Century Pulp & Paper is continually working in response to customer requirements. The specification mentioned are therefore subject to change. Learn more about our upgraded specification sheet on our website : www.centurypaperindia.com
Date : 01.01.2024

Note : This specification supersedes all previous specification