

Parameter	Substance	Bulk	Breaking Length		Tear Factor		Stiffness		Cobb'60 Sec.	Bendtsen Roughness	Brightness ISO	Opacity	Wax Pick	Shade
			MD	CD	MD	CD	MD	CD						
Unit	gm/m ²	cc/gm	Meter	Meter	-	-	'Taber	'Taber	gm/m ²	ml/Min	%	%	No.	-
Century SS Drawing Paper	68-100	1.37(Min)	4500±400	2400±400	45±5	50±5	"Upto 80 gsm - 3.7±0.5 90 - 100 gsm - 5.5±0.5 110 gsm & above -10±0.5	Upto 80 gsm - 1.5±0.3 90 - 100 gsm - 3.5±0.3 110 gsm & above -6±0.5	23±2	450±150 /550±150"	88 ± 1(NS) 90±1(White)	Upto 70 gsm - 86±1 75 -90 gsm - 87±1 110 gsm & above -92±1	12A Clear	NS/White
Century Parchment	106-120	1.17(Min)	4400±400	2800±400	50±5	55±5	NA	NA	22±2	200±30 /250±30	88 ± 1	106 gsm - 88±1 120 gsm -90±1	12A Clear	Off White
Century MICR Cheque Paper	95	1.05(Min)	6500±500	3000±500	700 mN (Min)	700 mN (Min)	4.5±0.5	2.5±0.5	22±2	40±5 (sec/50 ml) Gurley	83±1	86±1	10A Clear	Natural
Century Non MICR	85	1.05(Min)	5500±500	2800±500	60±5	70±5	3.5±0.2	2.0±0.2	22±2	40±5 (sec/50 ml) Gurley	83±1	86±1	10A Clear	Natural
Century Overlay Tissue	45	1.17(Min)	7000±500	4000±500	65±5	75±5	NA	NA	NA	120±30/150±30	85±1	NA	NA	Natural
Century Azure Laid	58-95	58-70 -1.30 (Min) 80 -90 -1.22 (Min)	3800±400	2300±400	45±5	50±5	NA	NA	23±2	200±50/300±50 150±50/250±50"	NA	58-60 gsm - 84±1 65-70 gsm 86±1 75 & Above -88±1	NA	Green
Century Azure Laid	105	1.17 Min	3500±400	2300±400	45±5	50±5	NA	NA	23±2	150±50 250±50	88±2	93±1	NA	Light bluish
Maplitho ARSR (NS)	115 120-175	1.35(Min) 1.40(Min)	3400±400	2400±400	45±5	50±5	NA	NA	22±2	750±150/850±150	86±2	115 gsm - 91±1 120 gsm & above -93±1	NA	Natural
Cupstock Bottom	165	1.30 (Min)	4800±500	2300±500	55±5	60±5	45 ± 5 (mN)	25 ± 5 (mN)	22±2	650±150/750±150	86±2	NA	NA	Natural
Cupstock Wall	170	1.20 (Min)	5500±500	3000±500	65±5	70±5	60 ± 10(mN)	30 ± 10 (mN)	22±2	450±150/550±150	86±2	NA	NA	Natural
Coating Base (Wedding Card)	115-180	1.27 (Min)	5000±500	2500±500	45±5	50±5	NA	NA	22±2	450±150/550±150	86±2	115-120 gsm- 91±1 125-130gsm - 92±1 150-170 gsm- 94±1 175 & Above - 95±1	16 A Clear	Natural
Parameter	Substance	Bulk	Density	Water Klemm		COP at 35°C		Gurley Porosity		Wet Strength	Ash	pH		Shade
				MD	CD	I	II					Hot Extract		
Unit	gm/m ²	cc/gm	gm/cc	mm/4 min	mm/4 min	Sec	Sec	Sec/50 ml		gm/cm	%	-		-
Century Absorbent Kraft	150	1.45(min)	0.65-0.70	25±3	23±3	25±3	18±3	15-25		120 - 175	2.0-3.0	7.0-8.0		Natural Unbleached

An ISO 9001, ISO 14000 & OHSAS 18001 Company