

## Product Specification

S.No.	Properties	UOM	Century Bond
1	Substance	g/m <sup>2</sup>	85 ± 2.5%
2	*Bulk	cc/gm	1.35 ± 0.03
3	*Breaking Length	MD	6300 ± 500
		CD	3200 ± 500
4	*Tear Factor	MD	65 ± 5
		CD	70 ± 5
5	*Burst Factor	-	30 ± 2
6	Cobb <sub>60</sub>	g/m <sup>2</sup>	20 ± 2
7	Smoothness (Bendtsen)	I side	200 ± 30
		II side	280 ± 30
8	*ISO Brightness (L&W Elrepho)	%	96 ± 1
9	*CIE Whiteness (L&W Elrepho)	-	135 ± 5
10	*Print Opacity (L&W Elrepho)	%	90 ± 1
11	*Wax Pick	no.	16 A Clear
12	Stiffness	MD	4.5 ± 0.5
		CD	2.5 ± 0.5
13	Shade	-	Off White