

Product Specification

| S.No. | Properties | | UOM | 75 | | 80 | |
|-------|-------------------------------|---------|------------------|------------|--|------------|--|
| | | | | | | | |
| 1 | Substance | | g/m ² | 75 ± 2.5 % | | 80 ± 2.5 % | |
| 2 | Thickness | | micron | 100 ± 5 | | 102 ± 5 | |
| 3 | *Bulk | | cc/gm | 1.33±0.06 | | 1.28±.06 | |
| 4 | *Breaking Length | MD | meter | 4500 ± 400 | | 4600 ± 400 | |
| | | CD | | 3000 ± 400 | | 3000 ± 400 | |
| 5 | *Tear Factor | MD | - | 42 ± 5 | | 42 ± 5 | |
| | | CD | | 50 ± 5 | | 50 ± 5 | |
| 6 | Cobb ₆₀ | | g/m ² | 28 ± 2 | | 28 ± 2 | |
| 7 | Smoothness (Bendtsen) | I side | ml/min | 180±50 | | 180±50 | |
| | | II side | | 250±50 | | 250±50 | |
| 8 | *ISO Brightness (L&W Elrepho) | | % | 92 ± 1 | | 92 ± 1 | |
| 9 | *CIE Whiteness (L&W Elrepho) | | - | 155 ± 5 | | 155 ± 5 | |
| 10 | *Print Opacity (L&W Elrepho) | | % | 91 ± 1 | | 92 ± 1 | |
| 11 | *Wax Pick | | no. | 14 A Clear | | 14 A Clear | |
| 12 | *Stiffness | MD | ° Taber | 2.2 ± 0.2 | | 2.4 ± 0.2 | |
| | | CD | | 1.2 ± 0.2 | | 1.4 ± 0.2 | |
| 13 | Shade | | - | Bluish | | Bluish | |