

Product Specification

S.No.	Properties		UOM	Star	
				75	80
1	Substance		g/m ²	75 ± 2.5 %	80 ± 2.5 %
2	Thickness		micron	100 ± 5	102 ± 5
3	*Bulk		cc/gm	1.33±0.06	1.28±.06
4	*Breaking Length	MD	meter	4500 ± 400	4600 ± 400
		CD		3000 ± 400	3000 ± 400
5	*Tear Factor	MD	-	42 ± 5	42 ± 5
		CD		50 ± 5	50 ± 5
6	Cobb ₆₀		g/m ²	28 ± 2	28 ± 2
7	Smoothness (Bendtsen)	I side	ml/min	180±50	180±50
		II side		250±50	250±50
8	*ISO Brightness (L&W Elrepho)		%	92 ± 1	92 ± 1
9	*CIE Whiteness (L&W Elrepho)		-	155 ± 5	155 ± 5
10	*Print Opacity (L&W Elrepho)		%	91 ± 1	92 ± 1
11	*Wax Pick		no.	14 A Clear	14 A Clear
12	*Stiffness	MD	° Taber	2.2 ± 0.2	2.4 ± 0.2
		CD		1.2 ± 0.2	1.4 ± 0.2
13	Shade		-	Bluish	Bluish